



TECHNOVINYL POLYMERS(I)LTD.  
30, Unique Indl. Estate, Dr. Rajendra Prasad, Road, Mulund(W), Mumbai-400 080  
Tel.: 022-25930940/41/43/44. Fax: 022-25642577  
Email: [kk\\_group@vsnl.net](mailto:kk_group@vsnl.net) Website: [www.kkthelittlegiant.com](http://www.kkthelittlegiant.com)



## TECHNICAL DATA SHEET

### K-PRENE THERMOPLASTIC ELASTOMER LOW COMPRESSION SET FOR EPDM REPLACEMENT

PROPERTIES	UNIT	K PRENE GLC 6040	K PRENE GLC 6050	K PRENE GLC 6060	K PRENE GLC 6070
SPECIFIC GRAVITY	--	0.94 ± 0.02	0.94 ± 0.02	0.94 ± 0.02	0.95 ± 0.02
HARDNESS	SHORE A	40 ± 5	50 ± 5	60 ± 5	70 ± 5
TENSILE STRENGTH	Kg/cm <sup>2</sup>	30 ± 5	35 ± 5	40 ± 5	50 ± 5
ELONGATION AT BREAK	%	> 700	> 700	> 700	> 600
COLOUR	-	NATURAL	NATURAL	NATURAL	NATURAL
<b>COMPRESSION SET</b>					
AT 40°C	%	36	36	36	38
AT 70°C	%	42	42	42	45
AT 125°C	%	52	52	52	55
UV & SUNLIGHT RESISTANCE		YES	YES	YES	YES
OZONE RESISTANT		YES	YES	YES	YES
ACID & ALKALI AND CHEMICAL RESISTANT		YES	YES	YES	YES
OIL, FUEL & GREASE RESISTANT		NO	NO	NO	NO
HEAT RESISTANT UPTO 125°C		YES	YES	YES	YES
APPLICATION		EPDM REPLACEMENT RUBBER REPLACEMENT			

Manufactures Of :

Thermoplastic Elastomers

Hi Performance PVC Compounds

PP Compounds

Speciality Polymers