



TECHNOVINYL POLYMERS(I)LTD.
30, Unique Indl.Estate, Dr.Rajendra Prasad
Road, Mulund(W), Mumbai-400 080
Tel.: 022-25930940/41/43/44. Fax: 022-25642577
Email: kk_group@vsnl.net Website: www.kkthelittlegiant.com



TECHNICAL DATA SHEET

Product Code No. KK TC-A-98

Original Physical Properties	
Specific Gravity	1.38 (± 0.03)
Hardness Shore A	98 (± 3)
Tensile Strength MPa	22.8
Elongation at Break %	200
Heat Ageing : 7 days at 100°C	
Variation in Tensile Strength, %	± 25
Variation in Elongation, %	± 25
Loss of Mass, mg/cm ²	2
Thermal	
Thermal Stability @ 200°C, minutes	130 min.
Volatile Loss @ 130°C for 3 hrs, %	0.5 max.
Electrical	
Volume Resistivity, ohm.cm	8×10^{14}

Processing Temperature: 150°C to 185°C

Feature: Tele communication thin wall insulation.

Manufactures Of :
Thermoplastic Elastomers
Hi Performance PVC Compounds
PP Compounds
Speciality Polymers